PATENT ABSTRACTS OF JAPAN

(11)Publication number:

57-001232

(43) Date of publication of application: 06.01.1982

(51)Int.Cl.

H01L 21/316

(21)Application number: 55-075907

(71)Applicant: MITSUBISHI ELECTRIC CORP

(22)Date of filing:

(72)Inventor: MIZUGUCHI KAZUO

KINOSHITA SHIGEJI

ITO KAZUO DENDA MASAHIKO


(54) OXIDE FILM FORMING DEVICE

(57)Abstract:

PURPOSE: To delay the formation speed of an oxide film at a high temperature as well as to improve the uniformity and reproducibility of the oxide film of high quality by a method wherein the reaction chamber in which oxidized gas was induced is put in a decompressed condition and an oxidation by heat is performed on an Si wafer and the like under the decompressed condition.

04.06.1980

CONSTITUTION: For example, a plurality of Si wafers 3 placed on a boat 4 are put in a reaction chamber 1, oxidized gas is feeded from the lead-in port 5 provided at one end of the reaction chamber 1 and the reaction chamber 1 is decompressed (atmospheric pressure W0.1torr or thereabouts) from the other end using an exhaust system. The wafer 3 will be oxidized by heat under the decompressed condition, and as an oxidizing gas, the gas which is obtained by burning O2 or O2 and H2 that are diluted with the inert gas O2, N2 or Ar and the like and used. Through these procedures, as the



oxidation speed of the wafer 3 can be suppressed, the thin oxide film of high quality to be usee as the gate film of MOSLSI can be formed and the uniformity of the formed oxidation film inside the wafer and in between the wafer and the reproducibility between processing batch can be improved as well.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

(19) 日本国特許庁 (JP)

①特許出願公開

⑩公開特許公報(A)

昭57—1232

60Int. Cl.3 H 01 L 21/316 識別記号

庁内整理番号 7739-5F

❸公開 昭和57年(1982)1.月6日

発明の数 審査請求 未請求

(全 2 頁)

60酸化膜生成装置

20特 頭

昭55-75907

昭55(1980)6月4日 22出

明者 水口一男 勿発

> 尼崎市富松町4丁目22の1柏杉 寮内

木下繁治 明者 の発

> 伊丹市瑞原 4 丁目 1 番地三菱電 機株式会社エル・エス・アイ研 究所内

@発 明 者 伊藤和男

宝塚市安倉南1丁目11番5号

明 者 伝田匡彦 @発

> 伊丹市瑞原 4 丁目 1 番地三菱電 機株式会社エル・エス・アイ研

究所内

加出 願 人 三菱電機株式会社

東京都千代田区丸の内2丁目2

番3号

仍代 理 人 弁理士 葛野信一 外1名

明、 細

1. 発明の名称

酸化膜生成装置

2. 特許請求の範囲

(1) 被酸化物を収納し得る反応室、との反応室に 酸化性ガスを導入するガス導入口、上記反応室を 波圧する排気装置を 備え、上配被酸化物を 滅圧下 で酸化することを特徴とする酸化膜生成装置。

(2) 酸化性ガスとして02ガスを用いることを特徴 とする特許請求の範囲第1項記載の酸化膜生成装

(3) 酸化性ガスとして、02ガスにN2ガスまたは不 活性ガスを希釈して用いることを特徴とする特許 請求の範囲第1項記載の酸化膜生成装置。

(4) 酸化性ガスとしてHz ガス及びOz ガスを用いる ことを特徴とする特許請求の範囲第1項記載の設 化膜生成装置。

3. 発明の詳細な説明

との祭明は半導体装置において使用される酸化 籐の生成装置に関するものである。

現在、集積回路、特に MOB-FET 集積回路の高密 度化に伴い、微細なパターンのトランジスタを半 導体基板上に形成する事が要求されている。とれ に伴い、特に MOB 集積回路においてはゲート酸化 膜の薄膜化、例えば 64K ピットのダイナミック R AMにおいては 400~500Å のゲート酸化膜が使用さ カている。

更に高集積化、高密度化を行う場合、ゲート銀化 膜は更に薄くする必要がある。とのような薄い像 化膜を形成する方法としては、従来の装置として 第 1 図に示すものがあつた。

図において、1は酸化を行う反応管で材料として 例えば石英を用いる。2はクエハを高湿に保つヒ ーター、 3 は 表面 に 像 化 膜 を 生 成 すべ き 半 導 体 ク エハ、4は半導体を載せるポート、5はガス例え ば0:ガスの導入口である。

との方法において例えばゲート酸化膜としての 使用に耐える高品質の薄い酸化膜(例えば 1000点 以下)をウェハ内膜厚均一性、一括処理内ウェハ 間膜厚均一柱、再現性を保ちながら量産できる観

(2)

化膜の膜厚は約 400Åが限度である。時に高品質の 膜質を得る為には、高温(950で以上)である事が 必要であり、酸化膜例をは81上の酸化膜の生成選 度は 950 で、02がス流量 5 ℓ/分において 20Å/ 分以上あり、ポートの出し入れ時の酸化等の影響 による処理毎の膜厚のばらつきが無視できず、膜 厚の再現性が悪い。通常の処理枚数は 1 回処理当 り 100 枚種度が限度である。

又、 膜厚制御性を向上させる為に生成選度を下げるべく 温度を下げると 膜質が劣る欠点がある。

この発明は上記のような従来のものの欠点を除去する為になされたもので、酸化膜の品質を落さず、酸化膜の生成速度を抑削するために大気圧より低い圧力下で、酸化膜生成を行う事ができる酸化装置を提供する事を目的としている。

以下、との発明の一実施例を図について説明する。第2図において1は反応室を構成する反応管で、例えば材料として石英を用いる。2はクエハを加熱するヒーター、3は酸化膜を生成すべき被酸化物である半導体クエハ、(4)は半導体クエハを

(3)

第1図は従来の観化装置を示す側断面図、第2 図はこの発明の一実施例による減圧式観化装置を 示す側断面図である。

図において、1 は反応管、2 はヒーター、3 は 半導体ウエハ、4 はポート、5 はガスの導入口、 6 は排気装置である。

代理人 葛野 信一

・載せるポート、5 は酸化性ガス、例えば02ガスを 導入するガス導入口、6 は反応管内を滅圧にする 為の排気装置、例えばロータリポンプである。

この装置は減圧下(大気圧~ 0.1 Torr)で酸化を行うので、高温(900で以上)又は低温(900で以下)において、酸化膜の品質を落とさずに生成速度を避く(10 Å/ 分以下)して膜厚制御の向上を図り、処理毎の膜厚分布を抑え、 1 括処理内のウェハ間厚均一性を向上し得る。

なか、上記実施例にかいては、酸化時にOzガスのみを流したが、酸化速度を抑える万法として、Ozガスを希釈する万法がある。希釈ガスとして、従来Nzガスが使用されて来たが、熱伝導率の良いdeガス又はArガスを使用する事は、一括処理ウェハ内膜厚均一性を高める事に有効である。

又、酸化方法としてH2及びO2ガスを同時に流して、水常燃焼酸化法(約650℃以上で自然発火する。)があり減圧下においてもH2、O2ガスを同時に流してこれを行う事が可能である。

4. 図面の簡単な説明

(4)

